

Product Specification

Aluminum

Meets ASTM B209 standards.

Alloy or Equivalent:	3105 type
Density:	.170 lb/ft ³
Minimum Ultimate Tensile Strength:	25,000 - 28,000 psi
Minimum Ultimate Yield Strength:	21,000 - 24,000 psi
Minimum Elongation:	2 - 3%
Modulus of Elasticity:	10
Coefficient of Linear Expansion:	13.1 μ -in/in/°F
Melting Range:	1190 - 1210°F
Thermal Conductivity at 77°F:	1190 BTU-in/ft ² -hr-°F
Hardness (Rockwell 15T):	63-70
Thickness:	.016 inches - Trim coil .019 inches - Trim coil, soffit, fascia, drip edge, trim coil & accessories .024 inches - Trim coil, fascia & drip edge
Flexibility:	1T NC/NTO



888.784.0878
qualityedge.com

Michigan
2712 Walkent Drive NW
Walker, MI 49544

Georgia
5520 Export Blvd
Garden City, GA 31407

Texas
634 107th Street
Arlington, TX 76011

October 25, 2017