

ARCHITECTURAL SPECIFICATION

TRUCEDAR® STEEL SIDING



TruCedar siding is made from roll-formed 0.016" galvanized steel, complying with ASTM A653/A653M and has a minimum yield and ultimate strength of 33,000 and 55,000 psi. Finished product measures 12 ft. in length and is available in Single 6" & 8", Single 6" Dutch Lap, Double 4", and Board and Batten 6" & 10".

Coating Characteristics

Kynar® Paint System: 1.2 mil nominal film top coat and 0.4 mil backer with a gloss range of 6° to 12° on 60° photovolt meter.

Adhesion of Film

No blistering or loss of adhesion after immersion in distilled boiling water for a minimum of 4 hours followed by a minimum 4-hour freeze test.

Finish shall not be removed from cross hatched lines scored 1/8" apart after application of number 600 Scotch Tape.

Flexibility

Reverse impact: Garner impact tester—5/8" Steel Ball, 120 inch-pounds

Bending: OT 180° bend, 29-gauge steel

Elongation

Withstands 25-40% elongation

Tensile Strength

Complies with ASTM A653

Accelerate Tests

Humidity Cabinet: Panels given 90° bend and subjected to 100% relative humidity at 100°F (+/- 5°F) for 1,000 hours; no blistering, cracking, loss of gloss or peeling and no softening after 24-hour recovery.

Fire Rating

Complies with ASTM E84 Class A fire rating.

Salt Spray

When subject to a 5% salt solution (ASTM B117), shall withstand 1,000 hours exposure without blistering or loss of adhesion. QE warrants installations further than 1,500 ft. from the ocean.

Weatherometer

Tested in accordance with ASTM D822-57T after period of 2,000 actual light hours with humidity control shall show no cracking, crazing or loss of adhesion.

Chalking: No greater than ASTM D659-44 No.10 rating, based on a scale of 10 being excellent, no more than 8 Hunter E units.

Color Change (fade): No more than 5 Hunter E units

Recyclable

100% Recyclable. Reduced gas emissions, energy consumption and landfill footprint.



800.784.0878
www.QualityEdge.com

Quality Edge Headquarters

2712 Walkent Drive NW
Walker, MI 49544

Quality Edge Georgia

5520 Export Boulevard
Garden City, GA 31408

Quality Edge Texas

634 107th Street
Arlington, TX 76011